

**SECTION 071813****PEDESTRIAN TRAFFIC COATINGS****PART 1 GENERAL****1.01 SUMMARY**

- A. Section includes: Provides a complete multi-layer, cementitious roof and walking deck system for concrete surfaces that meets the requirements for specific use indicated in the contract documents. Include all applicable substrate testing, surface preparation, and detail work.

**1.02 RELATED SECTIONS**

- A. Section 030000 – Concrete
- B. Section 050000 – Metals
- C. Section 060000 – Wood, Plastic, and Composites
- D. Section 080000 – Openings
- E. Section 090000 – Finishes
- F. Section 220000 – Plumbing

**1.03 REFERENCES**

Shur Deck over concrete meets:

- A. IAPMO evaluation for Class A fire retardant, durability, and wind resistance. IAPMO Evaluation Report # 517
- B. ASTM 1242A
- C. ASTM E-108
- D. ASTM C-109
- E. ASTM C-67-03a
- F. ASTM C-297
- G. ASTM C-794
- H. ASTM D-412
- I. ASTM D-570
- J. ASTM D-756
- K. ASTM D-2047
- L. ASTM D-2240
- M. AC 308/ Section 4.3
- N. AC 308/ Section 4.8

**1.04 SUBMITTALS**

- A. Submit under provisions of Section 013300.
- B. Product Data: Submit manufacturer's product data sheets on each product and system to be used including:
  - 1. Preparation instructions and recommendations.
  - 2. Storage and handling requirements.
  - 3. Installation methods.
  - 4. Maintenance requirements.
- C. Selection Samples: For each system specified, provide two sets of samples and color charts representing manufacturer's full range of colors and patterns.

**1.05 QUALITY ASSURANCE**

- A. All materials used in the pedestrian traffic system shall be manufactured and provided by a single manufacturer to ensure compatibility and proper bonding.
- B. Use adequate numbers of skilled workmen thoroughly trained and experienced in the necessary crafts and completely familiar with the specified requirements and methods needed for proper performance of the work of this section.
- C. Contractor shall have a minimum of 3 years experience installing pedestrian traffic coatings of this type which is required for this project and who is acceptable to the manufacturer.
  - 1. Applicator shall designate a single individual as project foreman who shall be on site at all times during installation.
  - 2. Contractor must show and have QCA Qualified Contractor/Applicator paperwork from the manufacturer of the coating system, as required to obtain a long-term jobsite specific warranty.
- D. Convene a pre-application meeting before the start of application of coating system. Require attendance of parties directly affecting work of this section, including: Architect, contractor, applicator, and authorized representative of the coating system manufacturer and interfacing trades. Review the following:
  - 1. Drawings and specifications affecting work of this section.
  - 2. Protection of adjacent surfaces.
  - 3. Surface preparation and substrate conditions.
  - 4. Application.
  - 5. Field quality control.
  - 6. Protection of coating system.
  - 7. Repair of coating system.
  - 8. Coordination with other work.

#### 1.06 DELIVERY, STORAGE & HANDLING

- A. Delivery: Materials shall be delivered to the job site in sealed, undamaged containers. Each container shall be clearly marked with manufacturer's label showing type of material, color, and lot number.
- B. Storage: Store all materials in a clean, dry place with a temperature range in accordance with manufacturer's instructions.
- C. Handling: Handle products carefully to avoid damage to the containers. Read all labels and Material Safety Data Sheets prior to use.

#### 1.07 PROJECT SITE CONDITIONS

- A. Maintain environmental conditions (temperature and weather) within the limits recommended by the manufacturer.
- B. Schedule coating work to avoid rain and excessive dust and airborne contaminants. Protect work areas from moisture and excessive airborne contaminants during coating application.
- C. Before any work is started, the applicator shall examine all surfaces for any deficiencies. Should any deficiencies exist, the architect, owner or general contractor shall be notified in writing and any corrections necessary shall be made.

#### 1.08 WARRANTY

- A. Upon completion of the work in this section provide a written warranty from the manufacturer against defect of materials for a period of 5 (five) years. To obtain project specific warranty the coating system applicator must be a Mer-Ko by Westcoat Qualified Contractor/ Applicator and apply for warranty.

## PART 2 PRODUCTS

### 2.01 MANUFACTURERS

- A. Acceptable manufacturer: Mer-Ko by Westcoat; 4007 Lockridge Street, San Diego, CA 92102. Telephone 844-537-7203. Fax 619-262-8606. Website: mer-ko.com

### 2.02 MATERIALS

- A. As basis of design Mer-Ko Shur Deck (no substitutions will be accepted): A multi-layer, cementitious roof and walking deck system designed for use over plywood or concrete substrates.

### 2.03 COMPONENTS

- A. Shur Deck System over Concrete: Waterproof walking deck system for use over concrete substrates, IAPMO # 517.
1. Base Coat: Combine one 50lb bag of MK-5 Shur Deck Cement with 1-1.5 gallons of water. Apply by trowel at a rate of 80-90 ft<sup>2</sup> per batch.
  5. Mer-Ko Membrane with Fabric Reinforcement (Flashing): Apply a thick coat of MK-25 Mer-Ko Membrane onto the vertical and adjacent horizontal surface using a brush or roller at a rate of 100-150 ft<sup>2</sup> per gallon. While the material is still wet, place the MK-80 Mer-Ko Burlap fuzzy side down into the wet MK-25, overlapping successive runs of fabric edges and ends a minimum of 2 inches.
  6. Mer-Ko Membrane with Fabric Reinforcement (Deck): Install the MK-75 Mer-Ko Lath to the horizontal surfaces. Pour the MK-25 Mer-Ko Membrane onto the MK-75, smooth trowel and back roll at 65 ft<sup>2</sup> per gallon to completely cover the MK-75. Apply an additional coat of the MK-25 over the entire surface at a rate of 150 ft<sup>2</sup> per gallon by trowel or roller.
  7. Body Coat : Combine 1 to 1.25 gallons of water to one 50 lb bag of MK-5 Shur Deck Cement. Trowel the material over the dry membrane surface at a rate of 90 ft<sup>2</sup> per mix. Allow the first coat to dry for a minimum of 2 hours before applying the second coat. Repeat the process for the 2nd coat as mentioned above
  8. Topcoat: Apply desired color of the MK-40 Mer-Ko Topcoat in two coats. Thin the 1st coat with 25% water and apply at the rate of 300 ft<sup>2</sup> per gallon. Allow to dry for 2 hours at 70°F, 50 percent relative humidity. The 2nd coat must be applied neat. Apply the second coat of the MK-40 perpendicular to the first at the rate of 200 ft<sup>2</sup> per gallon.

### 2.04 ACCESSORIES

- A. Supplemental Materials:
1. Flashing shall be minimum 26 gauge bonderized sheet metal. 4" x 6" inch at wall to deck juncture and 4" x 2" drip edge at outside perimeter of deck. Caulk all flashing seams and overlaps using MK-90 Polyurethane Caulking. (Note: If the flashing is not bonderized, it must be prepared in accordance with SSPC-SP11 surface preparation standards, in order for the coating to adhere properly).
  2. Westcoat's WP-47A Seam Tape may be used over all cracks and seams. Apply Westcoat's EC-72 Epoxy Patch Gel into the tape with a trowel or putty knife to smooth and broadcast with 30 grit silica sand to allow adhesion of the coating.
  3. Concrete repairs can be made with MK-5 Shur Deck Cement or MK-10 Mer-Ko Underlayment Cement as needed.
  4. WP-47-3 Seam Tape for crack repair.
  5. Optional Slip Resistance: MK-86 Slip Resistant Additive added to topcoat.
  6. Optional Smooth Finish: MK-6 Shur Deck Fine Cement can be used in lieu of the MK-5 at 150-200 square feet per batch, depending on the desired texture and finish.

## **PART 3 EXECUTION**

### **3.01 EXAMINATION**

- A. Verification of conditions.
  - 1. Inspect all surfaces to receive the pedestrian traffic system. Verify that surfaces are dry, clean, and free of contaminants that would prevent coating system from properly adhering to the surface.
  - 2. Verify that substrates have ¼ inch slope per linear foot.
  - 3. Before starting work, report in writing to the owner any unsatisfactory conditions.

### **3.02 SURFACE PREPARATION**

- A. General:
  - 1. Prepare surfaces using methods recommended by the manufacturer for achieving the best result for the substrate under the project conditions.
- B. Concrete substrate:
  - 1. Create a surface profile by grinding, water blasting, or shot blasting to achieve a surface profile equal to CSP 3 as specified by ICRI.
  - 2. Rout and clean cracks and static joints: fill with manufacturer's recommended flexible epoxy filler material.
  - 3. Honor all moving and expansion joints. Seal with manufacturer's recommended joint sealant.
  - 4. Repair any non-moving surface deviations with manufacturer's recommended patching material.

### **3.03 INSTALLATION**

- A. Install coatings in accordance with manufacturer's instructions.
- B. Mix all materials in accordance with manufacturer's instructions.
- C. Use application equipment, tools, and techniques in accordance with manufacturer's instructions.
- D. Uniformly apply coatings at spread rates and in number of coats to achieve specified coverage.
- E. Adhere to all limitations, instructions, and cautions for pedestrian coatings as stated in the manufacturer's published literature.

### **3.04 FIELD QUALITY CONTROL**

- A. Verify coatings and other materials are as specified.
- B. Verify coverages and finish of the system as work progresses.
- C. Manufacturer's representative shall provide technical assistance and guidance for surface preparation and application of coating systems.

### **3.05 PROTECTION AND CLEAN-UP**

- A. Installation areas must be kept free from traffic and other trades during the application procedure and cure time.
- B. Protect finished surfaces of coating system from damage during construction.
- C. Touch-up, repair or replace damaged coating system after substantial completion.
- D. Clean area and remove all debris upon completion of work. Dispose of empty containers properly according to current Local, State and Federal regulations.
- E. Allow material to cure 4 to 6 hours before light pedestrian traffic is permitted, 24 hours before heavy traffic and an additional 48 hours before heavy objects are placed on the surface.

### **3.06 MAINTENANCE**

- A. Contractor shall provide to owner, maintenance and cleaning instructions for the waterproof decking system upon completion of work. Owner is required to clean and maintain the surfaces to maintain manufacturer's warranty.

## END OF SECTION

*This guide specification has been prepared by Mer-Ko by Westcoat to assist design professionals in developing a project specific specification. This guide is a template that must be reviewed and adapted by specifiers to comply with project requirements. This guide specification is not to be copied directly into a project specification manual without review.*